



Cactus® Double Coated Film Tape

Technical Data Sheet No.Y291M

Product Information

Cactus® Double Coated Film Tape Y291M offers a moderate initial tack and peel adhesion, made up of 2 types of adhesive systems: a permanent solvent acrylic adhesive on the open side and a removable solvent acrylic adhesive on the closed side to perform clean removal with no adhesive residue.

Composition & Physical Properties

Adhesive System	: Solvent Acrylic	Tape Thickness	: 3.5 mil (0.09 ± 0.005 mm)
Carrier	: 1 mil PET	Tack J. Dow No.	: Open Side 7 Closed Side 14
Liner Thickness	: 4.7 mil	Peel Adhesion PSTC-3	: 49.4 oz/inch (1.4kg/25mm) 7.05±3.5 oz/inch (0.2±0.1 kg/25mm)
Liner Density/Material	: # 76 (120 g/m ²) PE Coated Bleached Kraft Paper	Shear Strength PSTC-7	: Over 24 hrs with 35.3 oz loading on 1" x 1" (1.0kg/25mm x 25mm)
Liner Color	: White	Heat Resistance	: Over 24 hrs with 17.6 oz loading on 1" x 1" (0.5 kg/25mm x 25mm) bonding 2 stainless steel plates at 176°F (80°C)
Tape Color	: Clear	Service Temperature	: -4°F ~ 212°F (-20°C ~ 100°C)

Applications

- Permanent adhesive : Specifically formulated to bond with low energy surface materials, like PE & PP, providing moderate adhesion to most substrates.
- Removable adhesive : Designed to provide a light bond with a variety of surfaces and clean removal without adhesive residue. This adhesive system offers re-usability when bonded to clean surfaces.
- Major applications :
 - a) Temporary bonding of posters, signs, banners, or other items that require light-duty bonding and clean removal
 - b) Laminated on rebound rubber or other foam/cork materials as shipping pads, to protect glasses during transportation. The removable adhesive leaves no ghosting on glasses.

Disclaimer and Limitation of Liability

In no event shall V. Himark USA and its employees be liable for any direct or indirect, special, incidental or consequential damage resulting from the use of this product. Therefore, it is strongly recommended that the user performs a test application first to determine the suitability of this product for the intended method of application.